

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Big Quokka Pty Ltd
26 Terra Cotta Drive
Blackburn VIC 3130

Test Number : 24-001971
Issue Date : 18/06/2024
Print Date : 18/06/2024

Sample Description Clients Ref : "Evertex Essence Collection 140mm Groove Board"
Decking Board
Colour : Brown
End Use : Outdoor Decking
Nominal Composition : Poly(vinyl chloride)(PVC) .47%, Poly(methacrylate) (PMMA) 6.5%
Fatty acid ester/.Benzophenone UV absorber/.2-Ethylhexyl
mercaptoacetate/.Wax.2%
Calcium carbonate/wood .39%, Titanium dioxide/asa.5.5%
Nominal Mass per Unit Area/Density : 0.86g/m2
Nominal Thickness : 24mm



323871

70951

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

Fiona McDonald

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Big Quokka Pty Ltd
26 Terra Cotta Drive
Blackburn VIC 3130

Test Number : 24-001971
Issue Date : 18/06/2024
Print Date : 18/06/2024

AS 4586-2013
Appendix A

Slip Resistance Classification of new Pedestrian Surface Materials

Wet Pendulum Test Method

Date of Testing	14-06-2024				
Operator	AWTA Test Operator 4				
Test Temperature (20±5degC)	21 °C				
Sample washed with pH neutral detergent and dried					
Test Direction	Length				
Fixed/Unfixed	Unfixed				
Slider No 96 Batch No	23				
Length	1	2	3	4	5
British Pendulum number	51	52	50	51	50
Classification	P4				

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 11/10/2023
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

323871

70951

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

Fiona McDonald

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Big Quokka Pty Ltd
26 Terra Cotta Drive
Blackburn VIC 3130

Test Number : 24-001970
Issue Date : 19/06/2024
Print Date : 25/06/2024

Sample Description Clients Ref : "Evertex Legacy Porch Flooring 152mm Board"
Decking Board
Colour : Brown
End Use : Outdoor Decking
Nominal Composition : Poly(vinyl chloride)(PVC) .47%, Poly(methacrylate) (PMMA) 6.5%
Fatty acid ester/.Benzophenone UV absorber/.2-Ethylhexyl
mercaptoacetate/.Wax.2%
Calcium carbonate/wood .39%, Titanium dioxide/asa.5.5%
Nominal Mass per Unit Area/Density : Approx: 19.5kg/m2
Nominal Thickness : 22mm



324390

70950

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

Fiona McDonald

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTa Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Big Quokka Pty Ltd
26 Terra Cotta Drive
Blackburn VIC 3130

Test Number : 24-001970
Issue Date : 19/06/2024
Print Date : 25/06/2024

AS 4586-2013
Appendix A

Slip Resistance Classification of new Pedestrian Surface Materials

Wet Pendulum Test Method

Date of Testing	19-06-2024					
Operator	AWTA Test Operator 14					
Test Temperature (20±5degC)	20 °C					
Specimens washed with pH Neutral Detergent and then dried						
Test Direction	Length					
Fixed/Unfixed	Unfixed					
Slider No 96 Batch No	23					
Length	1	2	3	4	5	SRV
British Pendulum number	52	51	53	52	51	52
Classification	P4					

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 11/10/2023
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

324390

70950

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTa Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTa Product Testing and AWTa Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTa Ltd.

Fiona McDonald

APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR